

## KOROLITE® GRAPHITE EXPANDED POLYSTYRENE (GPS) INSULATION

### PRODUCT DESCRIPTION

Korolite® Graphite Expanded Polystyrene (GPS) is a high-performance, closed cell, rigid foam insulation material that uses air as main ingredient. GPS insulation resists moisture and mold/fungi growth with low environmental impacts, high & stable Long-Term Thermal Resistance, and good drying potential over the long service lives of buildings. Korolite® GPS is used in many residential and commercial construction applications such as wall, roof and below-grade insulation including under slabs.

Korolite® GPS is an advanced combination of Graphite nanoparticles and Expanded polystyrene (EPS) creating an energy-efficient and cost-effective insulation solution for architects, builders and contractors.

### SIZES

Common widths and lengths are 2'x8', 4'x4' and 4'x8' [0.61m x 2.44m, 1.22m x 1.22m and 1.22m x 2.44m] but can be custom ordered in any size to meet your project specifications.

Common thicknesses are: 1", 1.5", 2", 2.5", 3", 4", 5" and 6" [25.4mm, 38.1mm, 50.8mm, 63.5mm, 76.2mm, 101.6mm, 127mm and 152.4mm] but can be custom ordered in any size, including factory-tapered, to meet your project specifications.

### MANUFACTURER

Airfoam Industries Ltd.  
19402 - 56 Ave, Surrey BC V3S 6K4 Canada  
800.663.8162 or 604.534.8626 | [www.airfoam.com](http://www.airfoam.com)

### CODE COMPLIANCE

Korolite® GPS insulation is Thermal Insulation with Surface Burning Characteristics. Korolite® GPS complies with CAN/ULC-S102.2.

#### Surface Burning Characteristics

CAN/ULC-S102.2: Flame-Spread Rating ≤290,  
Smoke Developed Classification over 500.

### FIRE CHARACTERISTICS

Limiting Oxygen Index: min. 24% per ASTM D2863.

Airfoam's GPS for construction applications contains a polymeric (non-HBCD) fire retardant modifier.

### MATERIAL PROPERTIES

Korolite® GPS Insulation products exhibit the typical physical properties indicated below when tested as represented.

### KOROLITE® GPS INSULATION - MATERIAL PROPERTIES

Property <sup>1</sup>	Units	Korolite® GPS Types				Test Standard	
		KG100	KG160	KG250	KG300		
Compressive Resistance <sup>2</sup>	psi	10	16	25	30	ASTM D1621 Proc.A	
Minimum @ 10% Deformation	kPa	70	110	172	207		
Thermal Resistance <sup>3,4</sup> Minimum @ 24°C [75°F]							
R-Value / inch thickness	ft²•hr•°F/(BTU•in)	4.7	4.7	4.7	4.7	ASTM D1621	
RSI / 25mm thickness	m²•°C/(W•25mm)	0.83	0.83	0.83	0.83		
Thermal Resistance <sup>3,4</sup> Minimum @ 4°C [40°F]							
R-Value / inch thickness	ft²•hr•°F/(BTU•in)	4.9	4.9	5.0	5.0	ASTM D1621	
RSI / 25mm thickness	m²•°C/(W•25mm)	0.86	0.86	0.88	0.88		
Flexural Strength	psi	25	35	50	51	ASTM C203 Proc. B	
Minimum	kPa	172	240	345	352		
Water Vapor Permeance <sup>4</sup>	perms	5.0	3.5	2.3	2.3	ASTM E96 desiccant	
Maximum @ 1" [25.4mm] thickness	ng/(Pa•s•m²)	287	201	132	132		
Water Absorption <sup>5</sup>	% by volume	USA	4	3	2	2	ASTM C272, 1 Day
Maximum		Canada	6	4	2	2	ASTM D2842, 4 Days
Density	Nominal <sup>6</sup> lbs/ft³	1	1½	2	2.15	ASTM C303 or D1622	
	Minimum kg/m³	14.4	21.6	28.8	32		
Dimensional Stability	% linear change max.			1.5		ASTM D2126, 7 Days @ 70±2°C	

<sup>1</sup> The test methods used to determine the material properties provide a means of comparing different cellular plastic thermal insulations. They are intended for use in specifications, product evaluations and quality control, but they are not intended to predict end-use product performance.

<sup>2</sup> The elastic limit is between 1% and 2% strain. Compressive resistances at 10% strain are provided for applications where the intended end-use can tolerate plastic (permanent) deformation under load.

<sup>3</sup> R means resistance to heat flow. The higher the R-value, the greater the insulating power.

<sup>4</sup> Values are for 1 inch or 25mm thick samples with natural skins intact. Better values will result for thicker materials.

<sup>5</sup> The lab-test methods for water absorption use complete submersion under a head of water for 24 or 96 hours, so the values are applicable to specific design requirements only when the end-use conditions are similar to test method requirements.

<sup>6</sup> Not part of all the industry consensus standards (ASTM C578, CAN/ULC-S701) and provided AS-IS solely for informational purposes.

### FIRE PROTECTION

**CAUTION:** This product is combustible. Keep away from high heat and ignition sources. A protective barrier or a thermal barrier is required as specified in the appropriate building code.

### ENVIRONMENT DATA

GPS has much lower environmental impacts than most other foam plastic insulation materials. The **Environmental Product Declaration (EPD)** has been certified by UL Environment and is available on [www.airfoam.com](http://www.airfoam.com).

Korolite® GPS insulation may contain up to 30% pre-consumer recycled content or can be ordered without recycled content for EIFS/Stucco applications.

Korolite® GPS insulation **resists mold & fungi growth** per ASTM C1338 and has no nutritional value for insects. To protect against termites place adequate physical barriers such as membranes around below-grade GPS.

**Max. service temperature:** Long-Term Exposure 75°C [167°F], Intermittent Exposure 80°C [176°F]

**Thermal expansion coefficient:** 5-7 • 10<sup>-5</sup>/°K

**Capillarity:** None.

### SOLUBILITY & INCOMPATIBILITY

Insoluble in water and in general chemically inert. GPS dissolves in hydrocarbons (e.g. fuels, oils, tar), organic solvents (e.g. acetone/ketones, benzene, paint thinner), ethers, esters, aldehydes and amines.

### JOBSITE STORAGE & INSTALLATION

When storing Korolite® GPS insulation products on the job site, care should be taken to keep exposed insulation protected from reflected sunline or prolonged solar exposure. If possible, store in-doors. During the construction process, avoid leaving Korolite® GPS surfaces uncovered in areas where 'reflective solar energy' is expected to be present such as near metal or glass reflective surfaces.

Install Korolite® GPS insulation in compliance with all applicable building codes. Korolite® insulation is easy to handle and install and can be cut with a utility knife or any sharp blade. Butt edges and ends tightly to adjacent GPS boards. Ensure compatibility of any other product (such as adhesives, tapes, coatings or finishes) with Expanded Polystyrene. Korolite® Rigid Foam Insulation is a non-structural material. Korolite® insulation shall only be placed into an assembly where the moisture transport mechanisms are well understood and determined to be acceptable in accordance with accepted engineering practice (e.g. current ASHRAE Handbook of Fundamentals).

For safe handling and storage information refer to the Safety Data Sheet (SDS) at [www.airfoam.com/SDS.pdf](http://www.airfoam.com/SDS.pdf) or request a printed copy.

**GHS Classification:** Non-Hazardous.


**UV-light surface degradation:** Avoid prolonged Korolite® GPS exposure to direct sunlight. The ultraviolet light creates a yellow dust on the surface of GPS products which has negligible impact on the products' properties but may require removal before adhering other materials such as stucco or self-adhesive membranes.

### AVAILABILITY

Korolite® GPS insulation is supplied from Surrey BC through our extensive distribution network. For product availability or to get in touch with your local distributor, call Airfoam at 800.663.8162 or +1.604.534.8626.

**Please contact us for a free estimate or additional information.**

**NOTICE:** Airfoam assumes no obligation or liability for the information in this document. Neither Airfoam nor its employees, representatives, or resellers make any representation or warranty, express or implied, whether arising by statute, operation of law, custom of trade or otherwise, with respect to the accuracy or completeness of information contained in this document or its fitness for any particular purpose, nor do they assume any liability for damages or injury resulting from the use of such information. ALL IMPLIED WARRANTIES INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.



### WARRANTY

Airfoam offers a **30-year limited warranty** for Korolite® GPS Insulation **including retention of 100% of its R-value**. See [www.airfoam.com/Korolite-Insulation-30-Year-Limited-Warranty.pdf](http://www.airfoam.com/Korolite-Insulation-30-Year-Limited-Warranty.pdf) and [www.airfoam.com/terms](http://www.airfoam.com/terms) for Terms and Conditions of Sale.

### MAINTENANCE

No maintenance is required in normal use. GPS insulation that became wet can be dried out within reasonable times per ASTM C1512 tests using adequate drainage and/or ventilation.

### RECYCLING



Graphite Expanded Polystyrene (GPS) can be recycled for reuse in a variety of different applications, from construction and landscaping to packaging and park benches. Airfoam Industries Ltd. is a registered Recycling Facility accepting recyclable #6 Graphite Expanded Polystyrene (GPS) from our customers - free of charge, if it is clean, dry, and not mixed with any other materials.

### TECHNICAL SERVICES

Airfoam can provide technical information and support to help address questions when using Korolite® GPS insulation. Technical personnel are available to assist with any insulation project. For technical assistance, contact Airfoam at:

Online: [www.airfoam.com/EPS-Insulation-Support.php](http://www.airfoam.com/EPS-Insulation-Support.php)

Phone: 800.663.8162 or +1.604.534.8626

Fax: +1.604.534.1212



**Airfoam Industries Ltd.**

19402 - 56 Ave, Surrey BC V3S 6K4 Canada

800.663.8162 or 604.534.8626

[www.airfoam.com](http://www.airfoam.com)